

## C3 60 MIL TECHNICAL DATA

CHARACTERISTICS	ASTM TEST METHOD	PHYSICAL PROPERTIES
<b>Color</b>		White (top) / Grey(bottom)
<b>Roll Size</b>		78" wide x 90' long
<b>Weight</b>		6.1 oz/ft <sup>2</sup> (nominal)
<b>Thickness</b>	ASTM D-751	60 mil (nominal)
<b>Breaking Strength</b> (minimum, lbs./in.)	ASTM D-751 (grab method)	300 lbs. X 300 lbs. <sup>1</sup>
<b>Seam Strength</b> (minimum % of breaking strength)	ASTM D-638	90%
<b>Elongation @ Break</b> (minimum, %)	ASTM D-751	35% x 40 % <sup>1</sup>
<b>Heat Aging</b> (minimum, %)	ASTM D-3045	80% x 80% <sup>1</sup>
<b>Tear Strength</b> (minimum. lbs.)	ASTM D-751 (Tongue Method)	100 lbs. X 100 lbs. <sup>1</sup>
<b>Low Temperature Bend</b>	ASTM D-2136	PASS (-40°F)
<b>Permeance</b>	ASTM E-96 (Procedure BW)	0.002 Perms
<b>Dimensional Change</b> (maximum %)	ASTM D-1204 (@ 176°F, 6 hrs.)	0.3%
<b>Dimensional Change</b> (maximum %)	ASTM D-1204 (@ 212°F, 1 hr.)	1.0%
<b>Water Immersion</b> (weight, change, Max %)	ASTM D-570 (@ 158°F, 1 week)	1.0%
<b>Hydrostatic Resistance</b> (min, psi)	ASTM D-751 (Method D)	400 psi
<b>Ozone Resistance</b>	ASTM D-1149	PASS
<b>EMMAQUA<sup>®</sup> Test</b>	ASTM E-838	PASS (2.7 million Langleys)

<sup>1</sup> This data is reported in Warp X Fill values.EMMAQUA<sup>®</sup> Test Method is a registered tradename of DSET Laboratories, Inc.

CONFIDENTIALITY NOTICE: This message is intended only for the use of the individual or entity to which it is addressed and may contain information that is privileged, confidential or exempt from disclosure under applicable law. If the reader of this message is not the intended recipient or the employee or agent responsible for delivering the message to the intended recipient, you are hereby notified that you are strictly prohibited from printing, storing, disseminating, distributing or copying this communication. If you have received this communication in error, please notify us immediately and please destroy this/these page(s).

Thank You, REPUBLIC POWDERED METALS, INC.