

C3 60 MIL RAM TECHNICAL DATA

REINFORCED ADHERED MEMBRANE FOR FULLY ADHERED ROOFING SYSTEMS

CHARACTERISTICS	ASTM TEST METHOD	PHYSICAL PROPERTIES
Color		White (top) / Grey(bottom)
Roll Size		76" wide x 90' long
Weight		10.2 oz/ft ² (nominal)
Thickness	ASTM D-751	60 mil (nominal)
Breaking Strength (minimum, lbs./in.)	ASTM D-751 (grab method)	350 lbs. X 325 lbs. ¹
Seam Strength (minimum % of breaking strength)	ASTM D-638	90%
Elongation @ Break (minimum, %)	ASTM D-751	25% x 30 % ¹
Heat Aging (minimum, %)	ASTM D-3045	80% x 80% ¹
Tear Strength (minimum, lbs.)	ASTM D-751 (Tongue Method)	100 lbs. X 100 lbs. ¹
Low Temperature Bend	ASTM D-2136	PASS (-40°F)
Permeance	ASTM E-96 (Procedure BW)	0.002 Perms
Dimensional Change (maximum %)	ASTM D-1204 (@ 176°F, 6 hrs.)	0.3%
Dimensional Change (maximum %)	ASTM D-1204 (@ 212°F, 1 hr.)	1.0%
Water Immersion (weight, change, Max %)	ASTM D-570 (@ 158°F, 1 week)	1.0%
Hydrostatic Resistance (min, psi)	ASTM D-751 (Method D)	500 psi
Ozone Resistance	ASTM D-1149	PASS
EMMAQUA[®] Test	ASTM E-838	PASS (2.7 million Langleys)

¹ This data is reported in Warp X Fill values.

EMMAQUA[®] Test Method is a registered tradename of DSET Laboratories, Inc.

CONFIDENTIALITY NOTICE: This message is intended only for the use of the individual or entity to which it is addressed and may contain information that is privileged, confidential or exempt from disclosure under applicable law. If the reader of this message is not the intended recipient or the employee or agent responsible for delivering the message to the intended recipient, you are hereby notified that you are strictly prohibited from printing, storing, disseminating, distributing or copying this communication. If you have received this communication in error, please notify us immediately and please destroy this/these page(s).

Thank You, REPUBLIC POWDERED METALS, INC.