

PRODUCT IDENTIFICATION

PERMAROOF[®] MB MINERAL

#400STDFR100 (sold by
pallet-20 rolls) 3' x 38' /
100 sq. ft. / roll
White granule surfacing

A GRANULE SURFACE MODIFIED BITUMEN CAP SHEET MEMBRANE

Description

PERMAROOF MB Mineral is a granule surfaced cap sheet membrane with fire resistant characteristics. It consists of specially selected bitumens, modified with compatible SBS elastomers and a glass reinforcing mat. PERMAROOF MB Mineral is also asbestos free. PERMAROOF MB Mineral meets ASTM D 6163, Type I, Grade G.

Uses

PERMAROOF MB Mineral is designed for application in both hot and cold applied roof systems where a granule surfaced membrane is desired.

Limitations

PERMAROOF MB Mineral is not intended to perform under ponding conditions. Positive drainage required. PERMAROOF MB Mineral is not to be exposed to solvents, oils or other contaminants harmful to asphaltic materials. You must back nail on all roofs with slopes 2:12 (2"/foot) or greater.

Advantages

PERMAROOF MB Mineral resists thermal shock and splitting. Meets building codes and insurance requirements. PERMAROOF MB Mineral has a factory applied surfacing which saves job site labor and application errors. PERMAROOF MB Mineral has a fire rating of Class A.

General Application

Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood

components, rooftop equipment which cannot be moved or shut down and numerous other conditions.

The following application information is designed to serve as a general guide. Detailed specifications should be prepared based upon each roof's conditions.

Structural Deck

Must be properly designed and structurally sound.

Drainage

Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains, and/or installing additional drains or tapered insulation.

Insulation

Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day.

Installation Procedures

According to job specifications, prepare the surface to be covered:

- Replace areas of wet insulation, deteriorated deck and wood components.
- Install roof insulation or nailed base sheet and multiply base ply system.

Cold Process PERMAROOF MB Mineral

For application in cold process adhesive, cut PERMAROOF MB Mineral in 16 to 18' lengths maximum. Allow lengths to relax.

Above 55°F: 30 minutes minimum

Below 55°F: 60 minutes minimum

TECHNICAL DATA

Thickness ASTM D 5147-97	120 mils 3.05 mm
Tensile Strength @ 0°F ASTM D 5147-95	120 lbf/in. MD 115 lbf/in. XMD
Elongation at 0°F ASTM D 5147-95	2.6% MD 2.5% XMD
Puncture Resistance ASTM E 154-88	70 lbf
Tear Strength @ 77°F ASTM D 5147-95	70 lbf MD 80 lbf XMD



Republic Powdered Metals, Inc.
2628 Pearl Road • Medina, OH 44256
www.rpmrepublic.com

PERMAROOF[®] MB MINERAL

Hot Applied PERMAROOF MB Mineral

Type IV Hot Asphalt is recommended as an adhesive for the PERMAROOF MB Mineral. Hot applied modified bitumen membranes require special application techniques under cool ambient temperatures and/or moderate wind conditions. Consult Republic Technical Department for specific recommendations.

Application

Plan the placement of PERMAROOF MB Mineral to ensure the water flows over or along, but not against, the exposed edges.

Starting at the low point of the roof, apply a uniform and continuous application of adhesive according to specifications. Embed ply sheets as specified. Avoid walking on plies during placement

Place PERMAROOF MB Mineral in a uniform and continuous application of adhesive. Lap selvage 4" minimum; end laps 6" minimum. Offset laps from base laps. Stagger ends 36" minimum. To assure complete and uniform adhesion, adhesive should exude past lap edges. Install flashings as specified.

Precautions

Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

Maintenance

A scheduled, periodic maintenance inspection of the PERMAROOF MB Mineral installation is recommended. Punctures may occur through mechanical damage, vandalism, etc., and should be attended to as quickly as possible. Always follow NRCA standards.

Technical Services

Advice on technical concerns may be solicited any time by contacting Republic Powdered Metals Inc. For project start-ups where the contractor has received material and the work is to commence, it is necessary to coordinate the involvement of Republic's Independent Sales Representative and Technical Field Service Department. A field service representative will be dispatched to the project for start-up assistance and final inspection to ensure a proper installation.



Republic Powdered Metals, Inc.
2628 Pearl Road • Medina, OH 44256
800/551-7081 • Fax: 800/382-1218

The information provided on this data sheet is effective as of October 2005 and supersedes all previous data concerning this product and its application.

© Republic Powdered Metals, Inc., 2005. All Rights Reserved.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Republic DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO REPUBLIC'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL REPUBLIC BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, REPUBLIC'S LIABILITY IS LIMITED, AT REPUBLIC'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.